

Errata to IEEE Recommended Practice for Marine Cable for Use on Shipboard and Fixed or Floating Platforms

Sponsor

International Marine Industry Committee

of the

IEEE Industry Applications Society

Correction Sheet

Issued 27 March 2008

Copyright © 2008 by the Institute of Electrical and Electronics Engineers, Inc. All rights reserved.
Published 2008. Printed in the United States of America.

This correction sheet may be freely reproduced and distributed in order to maintain the utility and currency of the underlying Standard. This correction sheet may not be sold, licensed or otherwise distributed for any commercial purposes whatsoever. The content of this correction sheet may not be modified. Contents of this correction sheet have been incorporated into the second printing of IEEE Std 1580-2001.

The metric value of 12.5 N/mm² should read as 12.4 N/mm² in the row of the following tables:

Page 29

Table 12—Insulation, electrical, and physical requirements; Types E, X, S, T, and T/N

Tensile strength, N/mm ² , min	8.2	4.8	12.4	12.4	5.5	13.8	13.8
---	-----	-----	------	------	-----	------	------

Page 31

Table 14—Insulation, electrical, and physical requirements for crosslinked polyolefin insulation (type P), voltage rating 0–2000 V

Tensile strength, N/mm ² , min	12.4
---	------

Page 35

Table 16—Jacket properties; type T, CP, N, and CPE

Tensile strength, N/mm ² , min	10.3	12.4	12.4	12.4
---	------	------	------	------

and Page 69

Table C.3—Low-smoke, halogen-free jacket properties: types L (XLPO) and TPO (TPPO)

N/mm ²	lbf/in ²
12.4	1800

Test potentials (V) should read as Test potentials (kV) as follows:

Page 37 (Table 19)

Table 19—High-voltage ac test potentials; type E, S, X, T, T/N, LSE, LSX and P cables

	Test potentials (kV)				
	0–300 V	301–600/ 1000 V	1001– 2000 V		2001–5000 V

Page 39

Table 21 Note A should read as follows:

^aCalculated from the formula $M = C^{(t-15.6)}$ in which C is determined as described in 5.17.4.2.6 and t is the temperature of the cable in °C.